


COMPATHERM[®] 9471 THERMAL INTERFACE MATERIAL



COMPATHERM[®] PAD

The 7 W/mK Nolato Compatherm[®] Thermal Interface Material 9471 is a performance product designed for demanding applications requiring high thermal conductivity in a very soft viscoelastic material.

Compatherm[®] Thermal Interface Material is naturally tacky on both sides, but can be coated on one side to remove the natural tackiness if needed.

TYPICAL MATERIAL PROPERTIES

PROPERTY	TEST STANDARD	UNIT	9471
Color	Visual		Pink
Thickness	ASTM D374	mm	1-5
Hardness	ASTM D2240	Shore00	40
Density	Helium Pycnometer	g/cm ³	3.10
Thermal conductivity	Hot Disk	W/mK	7.0
Dielectric Constant @ 1MHZ	ASTM D150		7.68
Dielectric Breakdown Voltage / mm	ASTM D149	VAC/mm	> 8000
Volume Resistance	ASTM D257		3.1*10 ¹²
Outgassing, TML	ASTM E595		0.3%
Outgassing, CVCM	ASTM E595		TBD

*Thickness tolerance, ±10% mm @ nominal thickness greater than 1mm; ± 0.1mm @ nominal thickness less than 1mm.

*Thirty second delay value shore 00 hardness scale.

Please Note:

Observed performance may vary in certain circumstances.
It is recommended that customers test the material with their specific applications.

FEATURES AND BENEFITS

- 7 W/mK thermal conductivity
- Guaranteed thermal performance
- Competitive price points to other thermal interface materials
- Soft and highly compressible for low stress applications
- Tacky both sides
- Thickness range from 0.5mm to 5mm stocked in the USA
- Offering quick turn converting in the USA and China

APPLICATIONS

- Cooling components to chassis, frame, or other mating components
- Memory modules
- Home and small office network equipment
- Mass storage devices
- Automotive electronics
- Telecommunication hardware
- Radios
- LED solid state lighting
- Power electronics
- LCD and PDP flat panel
- Set top boxes

MODUS ADVANCED TAKES
YOU FROM IDEA TO IGNITION



PICK A MATERIAL

LET MODUS CUT IT TO SIZE

COMPATHERM[®] 9471 THERMAL INTERFACE MATERIAL

DESIGN NOTES

It is recommended to use the material in up to 20%-30% of compression degree. A compression degree of 50% is possible to use but above that level is a thinner pad recommended. We recommend applying pressure slowly and evenly over the entire surface to achieve the highest performance and lowest thermal resistance.

ORDERING COMPATHERM[®]

Compatherm[®] materials are typically cut into custom shapes based on the application requirements. Modus stocks the full line of materials and can provide cut piece and kit prices based on your unique application. Cut pieces can be delivered kiss cut to a liner or through cut.

THICKNESS	SHEET SIZE	THERMAL RATING	NOLATO STYLE #	MODUS PART #
0.25MM	200MM x 200MM	7 W	9471	TM-280-6372
0.5MM	200MM x 200MM	7 W	9471	TM-280-6373
0.75MM	200MM x 200MM	7 W	9471	TM-280-6374
1MM	200MM x 200MM	7 W	9471	TM-280-6375
1.25MM	200MM x 200MM	7 W	9471	TM-280-6376
1.5MM	200MM x 200MM	7 W	9471	TM-280-6377
1.75MM	200MM x 200MM	7 W	9471	TM-280-6378
2MM	200MM x 200MM	7 W	9471	TM-280-6379

APPLICATION PROCEDURE

- Remove the top blue liner from the top surface of the sheet.
- Remove the cut part from the bottom blue liner.
- Place the part on the desired surface of heat sink, heat spreader or component.
- Compatherm's naturally tacky surface will adhere to the surface without having to apply excess pressure.
- Compatherm should not be removed and reused once it's been applied to a surface.

CUSTOMERS WHO USE COMPATHERM[®] MAY ALSO BE INTERESTED IN:

EMI SHIELDING

TriShield[®] **COMPASHIELD[®]**



CUSTOMERS ALSO SEARCHED:

gap filler	heat transfer pad
thermal material	thermal interface pad
thermal interface materials	thermally conductive pad
thermal putty	silicone gap filler
thermal conductive pad	conductive pads
gapfiller	thermal pad material
thermal gap pad	silicone thermal pad
thermal gap filler	thermally conductive rubber
thermal interface pad	thermal conductive pads
thermal materials	what is a thermal pad
thermal silicone	

THE NOLATO GROUP

Nolato is an advanced high-tech polymer partner with operations in Europe, Asia and North America. We develop and manufacture products in materials such as plastic, silicone and TPE. Our customer offering comprises everything from concept development, product design and process optimization to high-volume production, post-processing, assembly and logistics

ABOUT MODUS

We are Modus! With multiple locations in North America and China, Modus Advanced, Inc. is a diversified custom manufacturer that converts EMI Shielding, Environmental Gasket Materials, Microwave Absorbers, Acoustic Materials, Thermal Interface Materials and other high performance materials into finished parts. Modus utilizes its 40 years as an established provider of high quality, reliable products to create precisely what customers specify. Innovative processes; custom fabrication utilizing performance materials; an on time delivery record of more than 99% means Modus is well positioned to help your company succeed.

This information is based on data believed to be reliable, but Modus makes no warranties, expressed or implied, as to its accuracy and assumes no liability arising out of its use. The data listed falls within the normal range of product properties, but should not be used to establish specification limits or used alone as the basis of design. Modus' liability to purchasers is expressly limited to the terms and conditions of sales listed on our website.