



**COMMERCIAL NEOPRENE** 

# WESLASTOMER™ RC350-3500 RUBBER MOLDING COMPOUND



TYPICAL PROPERTIES	
Property	Value
Color	Black
Durometer (Shore A)	40
Density g/cm³	1.25
Tensile Strength Mpa	7
Elongation	500%
Tear Strength KN/m	22
Temperature Range	-40 to +110° C



## **APPLICATIONS**

- Industrial sealing and gasketing, especially when durability and pliability is required
- Automotive
- Military
- Agriculture
- Construction

#### **FEATURES AND BENEFITS**

- Excellent abrasion, oil, ozone, flame retardency and weather resistant
- Resistant to some chemicals

#### **AVAILABILITY**

· Custom molded into shapes



### CUSTOMERS ALSO SEARCHED:

custom molded rubber molded rubber china molded rubber USA molded rubber compression molded rubber rubber manufacturer custom injection molding custom compression molding custom molding custom molded silicone molded silicone molded gasket medical molding rubber to metal bonding custom molded rubber products custom rubber molding custom rubber production silicone molding neoprene gasket custom molded neoprene

MODUS ADVANCED TAKES YOU FROM IDEA TO IGNITION







IGNITION



We are Modus! With multiple locations in North America and China, Modus Advanced, Inc. is a diversified custom manufacturer that converts EMI Shielding, Environmental Gasket Materials, Microwave Absorbers, Acoustic Materials, Thermal Interface Materials and other high performance materials into finished parts. Modus utilizes its 40 years as an established provider of high quality, reliable products to create precisely what customers specify. Innovative processes; custom fabrication utilizing performance materials; an on time delivery record of more than 99% means Modus is well positioned to help your company succeed.

This information is based on data believed to be reliable, but Modus makes no warranties, expressed or implied, as to its accuracy and assumes no liability arising out of its use. The data listed falls within the normal range of product properties, but should not be used to establish specification limits or used alone as the basis of design. Modus' liability to purchasers is expressly limited to the terms and conditions of sales listed on our website.

WWW.MODUSADVANCED.COM •

SALES@MODUSADVANCED.COM

ABOUT MODUS